

CMP EPIPRIME MIO**Product description:**

A two-component polyamide adduct cured, anti-corrosive primer / midcoat containing Mio.

Typical use:

For use as a high build epoxy coating to improve barrier protection for a range of anti-corrosive coating systems in a wide range of environments including offshore structures, petrochemical plants, pulp and paper mills and bridges.

Suitable for use in both maintenance and new construction situations as part of an anti-corrosive coating system. The micaceous iron oxide variant improves long term overcoating properties, better facilitating application in the fabrication shop, prior to shipping, with final overcoating on site.

Certificates / approvals:

Certificates and approvals may be available on request.

ISO 12944-6 --> C4 h / C5 h

ISO 2812-1 --> chemical resistant

UNE 48271

Physical Data: (Mixed product)

Number of components:	Two Pack Product
Colours:	Grey and Red Brown
Gloss:	Low-gloss
Volume solids %:	73 ±2
Theoretical spreading rate:	7,3m ² /l
Flash point:	27°C (Mix)
Specific gravity:	2.32 kg/l
Dry to touch:	1.5 hour at 20 °C
Hard dry:	4.5 hours at 20 °C
VOC (Theoretical):	232 g/l

Recommended substrate conditions:

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2019.

Abrasive Blast Cleaning

Abrasive blast clean to Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of CMP EPIPRIME MIO, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

A surface profile of Rz5 40-75 microns is recommended.

Shop Primed Steelwork

CMP EPIPRIME MIO is suitable for application to unweathered steelwork freshly coated with zinc silicate shop primers.

If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary.

Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning.

Weld seams and damaged areas should be cleaned to a minimum St3 (ISO 8501-1:2007) Optimum performance will be achieved with blasting to Sa2½ (ISO 8501-1:2007)

Mixing

Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.

(1) Agitate Base (Part A) with a power agitator.

(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.

Application conditions

Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. Use only where application and curing can proceed at temperatures above: -5°C. The temperature of the paint itself should be: 15-25°C. In confined spaces provide adequate ventilation during application and drying. It is important that the surface is completely clean to ensure the adhesion. Any oil, grease, etc. to be removed by suitable detergent.

Application data:

Version, mixed products	CMP EIPRIME MiO
Recommended Thinner:	CMP EP THINNER
Mixing ratio:	Base: Curing agent: 274EE 274EE0000 80 : 20 (by volume) 89,7 : 10,3 (by weight)
Application method:	Airless spray, brush, roller*
Recommended thinner volume:	0 - 10% (by volume)
Nozzle orifice:	0.013 - 0.015"
Nozzle pressure:	18.0 - 25.0 MPa
Indicated film thickness, wet:	Min: 137µm
Indicated film thickness, dry:	Min: 100µm
Min. Temperature:	-5 °C
Pot life:	1.5 hours @ 20 °C
Surface temperature:	Dew point + minimum 3°C
Humidity:	85% R.H.
Overcoat interval, min:	See ADDITIONAL APPLICATION DATA
Overcoat interval, max:	See ADDITIONAL APPLICATION DATA

Add the Curing agent to the base whilst mixing. Stir well before use.

Notes: * In case of brush or roller application more layers may be required to achieve the specified film thickness.
When painting edges and welds, stripe coating is recommended.

Additional application data:

Application conditions:

Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. Use only where application and curing can proceed at temperatures above: -5°C. The temperature of the paint itself should be: 15-25°C. In confined spaces provide adequate ventilation during application and drying. It is important that the surface is completely clean to ensure the adhesion. Any oil, grease, etc. to be removed by suitable detergent.

Overcoating:

Overcoating intervals related to later conditions of exposure: If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion. Before overcoating after exposure in contaminated environment, clean the surface thoroughly with high pressure fresh water hosing and allow drying. A completely clean surface is mandatory to ensure intercoat adhesion, especially at long overcoating intervals. Any dirt, oil, grease, and other foreign matter must be removed with suitable detergent followed by (high pressure) fresh water cleaning. Salts to be removed by fresh water hosing. Any degraded surface layer, as a result of a long exposure period, must be removed. Water jetting may be relevant to remove any degraded surface layer and may also replace the above mentioned cleaning methods when properly executed. Consult Chugoku Paints B.V. for specific advice if in doubt. To check whether the quality of the surface cleaning is adequate, a test patch may be relevant. However, this test patch should not be a final proof of the durability of the coating systems. This may necessitate application of the product in reduced film thickness, down to: 50 micron/2 mils. For such purpose, addition of a thinner is recommended: CMP EP Thinner -> 5-10%.

Curing time and over-coating data:

Temp.	Surface dry (at 100µ DFT)	Hard dry (at 100µ DFT)	Fully cured (at 100µ DFT)	Over-coating Interval Min.	Over-coating Interval Max.	Pot life
-5 °C	14 hours	42 hours	7 days	20 hours	Extended	9 hours
0 °C	10 hours	25 hours	7 days	14 hours	Extended	7 hours
5 °C	5 hours	12 hours	7 days	7 hours	Extended	5 hours
10 °C	2.5 hours	6.5 hours	7 days	4 hours	Extended	3 hours
20 °C	1.5 hour	4.5 hours	7 days	3 hours	Extended	1.5 hours
30 °C	-	-	-	-	-	-

Spreading rates:

Dry Film Thickness	Theoretical Spreading rate
75 µm	9,7 m ² /l
100 µm	7,3 m ² /l
150 µm	4,9 m ² /l
200 µm	3,7 m ² /l

Storage:

Min. 24 months at 20°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. Elevated storage temperatures reduce shelf life.

Color variation:

When applicable, products may have slight color variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., and application quality. Contact your local Chugoku Paints B.V. office for further information.

Safety information: If Health, Safety and Environmental information is required a Health and Safety Data Sheet can be obtained from Chugoku Paints B.V.

Personal Protection advice and additional information can be obtained from the product Health and Safety Data Sheet which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist and vapours.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

Definitions:	Tolerances:	The numerical information quoted in this Technical Data Sheet is subject to normal manufacturing tolerances.
	Spreading Rate:	The spreading rate can vary depending on application conditions, the geometrical complexity of the structure, the weather conditions, etc.
	Volume Solids:	The volume solids figure given in this Technical Data Sheet is the percentage of dry film obtained from a given wet film thickness under specified application rate and conditions measured by the Chugoku Standard Method corresponding to ASTM method D2697 if not otherwise indicated.
	Overcoating Intervals:	The intervals given assume preparation consistent with good painting
	Hard dry:	The time taken until the product can be walked on without damaging it. Time taken until full mechanical strength is obtained is longer.
	V.O.C.:	Theoretical quantity of volatile organic compounds in g/l.

Disclaimer: Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam.

The Inspector will undertake to the best of their ability, to carry out assistance during application of the products delivered by Chugoku, by only rendering advice in connection with the application at site. The Inspector undertakes to carry out the project in a conscientious manner, but Chugoku and/or the Inspector will not accept any kind of liability, direct or indirect, if the project does not give the results expected. Under all circumstances, the Buyer remains responsible for the execution of the project. Any advice and/or assistance rendered by the Inspector will be subject to such (final) responsibility of the buyer, and moreover subject to the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. Even when damages or delays have been caused by faults or negligence on the side of Chugoku and/or the Inspector, such will not result in any liability whatsoever of Chugoku or the Inspector. Liability of both Chugoku or the Inspector for any consequential damages is explicitly excluded. Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.