

CMP EIPRIME MT

Product description:

CMP EIPRIME MT is a surface tolerant, high build epoxy coating with excellent physical properties such as adhesion and toughness. Product can be applied on every aged intact Epoxy or Polyurethane coating as long as DFT will not exceed 700 microns. It can even be applied on wet or damp surfaces which makes it ideal to apply after HP washing. It will stabilize rust on slightly corroded areas where optimum surface preparation is not possible. Expected service life using CMP EIPRIME MT for maintenance purposes is expected to be 7-years in case surface preparation is done according to CMP's application data.

Typical use:

As primer where HP Water washing is specified as surface preparation. It can be used as a primer/mid-coat when weather conditions do not permit the use of a traditional paint system. Can be used as a primer and mid-coat for a wide range of anti-corrosive coatings systems for use in the offshore, petrochemical, chemical, and bridge industries.

Certificates / approvals:

Certificates and approvals may be available on request.
ISO 12944-6 --> up to C5H

Physical Data: (Mixed product)

Number of components:	Two Pack Product	
Colours:	Light grey and Buff	
Gloss:	Semi-gloss	
Volume solids %:	72 ±2	(ISO 3233-3)
Theoretical spreading rate:	7,2m ² /l	
Flash point:	30°C (Mix)	(ISO 3679)
Specific gravity:	1.43 kg/l	
Dry to touch:	4 hours at 20 °C	(ISO 9117-4)
Hard dry:	12 hours at 20 °C	(ISO 9117-4)
VOC (Theoretical):	213 g/l	

Recommended substrate conditions:**Surface preparation:**

Minimum surface preparation should be high pressure water washing, with a suitable detergent to remove any contaminations (grease/oil)

Mixing

Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.

(1) Agitate Base (Part A) with a power agitator.

(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.

Application conditions

Use only where application and curing can proceed at temperatures above: 5°C. The temperature of the paint itself should be: 15-25°C. In confined spaces provide adequate ventilation during application and drying.

Application data:

Version, mixed products	CMP EIPRIME MT
Recommended Thinner:	CMP EP THINNER
Mixing ratio:	Base: Curing agent: 580EE 580EE0000 80 : 20 (by volume) 86 : 14 (by weight)
Application method:	Airless spray, brush, roller*
Recommended thinner volume:	0 - 15 %
Nozzle orifice:	0.019 - 0.023"
Nozzle pressure:	15.0 - 25.0 Mpa
Indicated film thickness, wet:	Min: 139µm
Indicated film thickness, dry:	Min: 100µm
Min. Temperature:	5 °C °C
Pot life:	50 min @ 20 °C
Surface temperature:	n/a
Humidity:	up to 100%
Overcoat interval, min:	See ADDITIONAL APPLICATION DATA
Overcoat interval, max:	See ADDITIONAL APPLICATION DATA

Add the Curing agent to the base whilst mixing. Stir well before use.

Notes: * In case of brush or roller application more layers may be required to achieve the specified film thickness.
When painting edges and welds, stripe coating is recommended.

Additional application data:

Application conditions:

Use only where application and curing can proceed at temperatures above: 5°C. The temperature of the paint itself should be: 15-25°C. In confined spaces provide adequate ventilation during application and drying.

Overcoating:

Overcoating intervals related to later conditions of exposure: Before overcoating clean the surface thoroughly with high pressure fresh water hosing. A complete clean surface is mandatory to ensure intercoat adhesion. Any dirt, oil, grease, salt, and other contamination must be removed with suitable detergent followed by (high pressure) fresh water cleaning. Consult Chugoku Paints B.V. for specific advice if in doubt. To check whether the quality of the surface cleaning is adequate, a test patch may be relevant. However, this test patch should not be a final proof of the durability of the coating systems.

Curing time and over-coating data:

Temp.	Surface dry (at 100µ DFT)	Hard dry (at 100µ DFT)	Fully cured (at 100µ DFT)	Over-coating Interval Min.	Over-coating Interval Max.	Pot life
-5 °C	-	-	-	-	-	-
0 °C	-	-	-	-	-	-
5 °C	18 hours	24 hours	7 days	24 hours	Extended	8 hours
10 °C	12 hours	18 hours	5 days	18 hours	Extended	6 hours
20 °C	4 hours	12 hours	3 days	12 hours	Extended	3 hours
30 °C	2 hours	7 hours	2 days	7 hours	Extended	1 hour

Note: Drying times and overcoating intervals will increase with increasing film thickness applied. Before re-coating, always check that the existing paint film is hard dry. Kindly consult with Chugoku sales representative.

Spreading rates:

Dry Film Thickness	Theoretical Spreading rate
100 µm	7,2 m ² /l
125 µm	5,8 m ² /l
150 µm	4,8 m ² /l
200 µm	3,6 m ² /l

Storage:

Min. 24 months at 20°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. Elevated storage temperatures reduce shelf life.

Color variation:

When applicable, products may have slight color variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., and application quality. Contact your local Chugoku Paints B.V. office for further information.

Safety information: If Health, Safety and Environmental information is required a Health and Safety Data Sheet can be obtained from Chugoku Paints B.V.

Personal Protection advice and additional information can be obtained from the product Health and Safety Data Sheet which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist and vapours.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

Definitions:	Tolerances:	The numerical information quoted in this Technical Data Sheet is subject to normal manufacturing tolerances.
	Spreading Rate:	The spreading rate can vary depending on application conditions, the geometrical complexity of the structure, the weather conditions, etc.
	Volume Solids:	The volume solids figure given in this Technical Data Sheet is the percentage of dry film obtained from a given wet film thickness under specified application rate and conditions measured by the Chugoku Standard Method corresponding to ASTM method D2697 if not otherwise indicated.
	Overcoating Intervals:	The intervals given assume preparation consistent with good painting
	Hard dry:	The time taken until the product can be walked on without damaging it. Time taken until full mechanical strength is obtained is longer.
	V.O.C.:	Theoretical quantity of volatile organic compounds in g/l.

Disclaimer: Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam.

The Inspector will undertake to the best of their ability, to carry out assistance during application of the products delivered by Chugoku, by only rendering advice in connection with the application at site. The Inspector undertakes to carry out the project in a conscientious manner, but Chugoku and/or the Inspector will not accept any kind of liability, direct or indirect, if the project does not give the results expected. Under all circumstances, the Buyer remains responsible for the execution of the project. Any advice and/or assistance rendered by the Inspector will be subject to such (final) responsibility of the buyer, and moreover subject to the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. Even when damages or delays have been caused by faults or negligence on the side of Chugoku and/or the Inspector, such will not result in any liability whatsoever of Chugoku or the Inspector. Liability of both Chugoku or the Inspector for any consequential damages is explicitly excluded. Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.